

Evaporation Retarder

ER-921

TECHNICAL DATA

1.0 DESCRIPTION

ER-921 is a surface-active agent used to reduce the water evaporation rate from the surface of newly laid concrete. It is designed to form a thin film to reduce rapid moisture loss from the concrete surface. ER-921 is spray applied in diluted form to fresh concrete flatwork to reduce the tendency for surface plastic cracking to occur. ER-921 aids and improves the workability and finishing characteristics of the concrete surface. ER-921 also helps extend the surface workability time for a given set of weather conditions.

2.0 PROPERTIES

2.1. Colour	Clear – Light Yellow
2.2. S.G.	1
2.3. Viscosity	Low
2.4. Toxicity	May be harmful if swallowed
2.5. D.G. Classification	Not hazardous for transport
2.6. Dilution Ratio	1 part ER-921 to 9 parts clean water. All references & instructions for ER-921 are for diluted product
2.7. Coverage	Up to 10m ² per litre (fully diluted)

3.0 USES

Use ER-921 as an evaporation retarder for concrete flatwork surfaces when the evaporation rate exceeds the bleeding rate. Recommended for use on all concrete surfaces except dry shake hardeners and toppings.

4.0 APPLICATION INSTRUCTIONS

- 4.1. Shake or stir before using. Dilute ER-921 as supplied at the ratio of 1 part ER-921 with 9 parts water.
- 4.2. Apply ER-921 with a commercial sprayer. Use a Chapin 8005 spray tip (or equivalent) that produces a fine mist.
- 4.3. Apply a fine mist to completely cover the concrete surface. ER-921 is most effective the sooner it is applied, for example, immediately after screeding and or between finishing operations.
- 4.4. When working in hot, dry conditions, ER-921 should be reapplied after each operation (floating, trowelling, etc).
- 4.5. Do not allow ER-921 to puddle. If puddling occurs, wipe up immediately and rinse with water.

ER-921

TECHNICAL DATA Continued

4.0 APPLICATION INSTRUCTIONS (continued)

- 4.6. Clean all equipment immediately after use with clean water.
- 4.7. Cure concrete with FRACURE or FRACURE EMULSION after bleed water or excess surface water has dissipated. ER-921 is NOT a curing compound. The protective film usually lasts as long as the concrete is plastic. For proper curing, use a FRACURE curing compound or water cure.

5.0 PRECAUTIONS

- 5.1. DO NOT USE ER-921 as a finishing aid for cementitious materials such as dry shake hardeners or toppings.
- 5.2. ER-921 should not be worked into the concrete surface nor should it be used to re-temper concrete.
- 5.3. ER-921 is not suitable for application onto vertical surfaces or where excessive ER-921 run-off may occur.
- 5.4. Keep away from frost. Keep all containers tightly closed when not in use. Refer to Product Safety Data Sheet for handling and safety details.
- 5.5. Stratmore Construction Solutions Limited is not responsible for compatibility with other manufacturer's products.

6.0 PACKAGING

ER-921 is supplied as 4, 20 & 200-litre concentrates.



**Strat
more.**

Leading solutions for construction.

The information contained in this data sheet, is to the best of our knowledge accurate and any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Users are urged to make their own assessment of our products under their own conditions and for their own requirements. Stratmore Construction Solutions Limited reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions. This data sheet may be updated without notice. Please ensure you have the latest copy. If you are a customer, then any contract with you is in accordance with our latest terms and conditions, which are available to download from our website. Where goods are acquired for business purposes, Parts 1 to 4 of the Consumers Guarantee Act 1993 will not apply. To the maximum extent permitted by law, we have no liability (whether statutory, in contract or tort, including negligence) to buyers, users or specifiers of our products for any physical, direct or indirect damage, economic loss or any other loss or costs caused or contributed by us or any of our agents or employees in respect of any goods or services supplied. Also to the maximum extent permitted by law, all conditions and warranties expressed or implied by statute or common law, equity, trade custom or usage or otherwise howsoever are excluded. If, notwithstanding the foregoing, Stratmore Construction Solutions Limited is found to have any liability, then it is agreed that the liability is nevertheless limited to the price of the relevant goods or services purchased from us.