

EPOXY GLUE EPAR GP

TECHNICAL DATA

1.0 DESCRIPTION

EPAR GP is a high strength, two-part epoxy glue. It is non-shrink and suitable for use where gap filling properties are required. EPAR GP having grease like viscosity, can be feathered out or applied up to 10mm thick on vertical surfaces. EPAR GP is suitable for service in either dry or wet conditions.

A fast-setting version is also available.

2.0 PHYSICAL PROPERTIES:

2.1	Viscosity	Grease-like, non-slump when mixed.
2.2	Mix Ratio	2 parts resin: 1 part hardener by volume.
2.3	Pot Life	25 minutes for 100 grams at 20°C.
2.4	Minimum Application Temp.	0°C.
2.5	Shelf Life	1 year.
2.6	Cured Properties	
2.6.1	Colour	Milky Yellow
2.6.2	Specific Gravity	1.1
2.6.3	Compressive Strength	68 MPa
2.6.4	Tensile Strength	33 MPa.
2.6.5	Thermal Expansion	5×10^{-5} mm/mm/°C.

3.0 USES

EPAR GP is suitable for use as a gap filling adhesive or filler for wood, concrete, steel, ceramics etc.

Fields of use include:

- Manufacture of timber joinery and furniture.
- Boat building.
- Repair and manufacture of formwork for concrete.
- Bonding and stopping of fibrous cement sheet.

4.0 APPLICATION INSTRUCTIONS

- 4.1 SURFACE PREPARATION. Thoroughly clean the jointing surfaces of all extraneous matter, especially oil and grease. Laitance should be removed from concrete surfaces mechanically or by acid etching. For best results steel surfaces should be prepared by sand blasting or grinding.

EPAR GP

TECHNICAL DATA Continued

4.0 APPLICATION INSTRUCTIONS (continued)

- 4.2 MIXING. Accurately proportion required volume of resin and hardener ensuring this amount can be used within its pot life. Large volumes of mixed EPAR GP will generate considerable heat and result in reduced pot life. If proportioning by eye, measure out 3 individual parts, two of resin and one of hardener. Estimating 2 parts, one twice the size of the other is very inaccurate.

Mix resin and hardener thoroughly using a spatula; larger volumes can be mixed using a mixing paddle on a low speed electric drill.

- 4.3 APPLICATION. When being used as an adhesive apply an even layer of EPAR GP to jointing surfaces preferably by notched trowel. The joint must be held in position until sufficient strength has been obtained. Initial set is between 2 and 6 hours depending on temperature.

When being used as a filler EPAR GP can be slightly overfilled and sanded back to obtain a smooth finish.

- 4.4 CLEAN UP. Tools and equipment may be cleaned before hardening commences by washing with EPAR Clean Up Solvent. Wash hands and skin with soap and hot water.

5.0 PRECAUTIONS

EPAR GP is not suitable for applications where the epoxy is directly exposed to weathering. Epoxy at the surface of a joint subjected to weathering will discolour/chalk over time but this will not affect the performance of the epoxy within the joint.

For maximum performance, allow a full 5 days curing before subjecting joints to stress.

EPAR GP hardener is corrosive to skin and eyes. Wear protective gloves and eye protection (if eye contact likely) when mixing and applying EPAR GP. Refer to product label and product safety data sheet for first aid and handling information.

6.0 PACKAGING

750ml, 1.5 litre and 3 litre packs.



The information contained in this data sheet, is to the best of our knowledge accurate and any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Users are urged to make their own assessment of our products under their own conditions and for their own requirements. Stratmore Construction Solutions Limited reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions. This data sheet may be updated without notice. Please ensure you have the latest copy. If you are a customer, then any contract with you is in accordance with our latest terms and conditions, which are available to download from our website. Where goods are acquired for business purposes, Parts 1 to 4 of the Consumers Guarantee Act 1993 will not apply. To the maximum extent permitted by law, we have no liability (whether statutory, in contract or tort, including negligence) to buyers, users or specifiers of our products for any physical, direct or indirect damage, economic loss or any other loss or costs caused or contributed by us or any of our agents or employees in respect of any goods or services supplied. Also to the maximum extent permitted by law, all conditions and warranties expressed or implied by statute or common law, equity, trade custom or usage or otherwise howsoever are excluded. If, notwithstanding the foregoing, Stratmore Construction Solutions Limited is found to have any liability, then it is agreed that the liability is nevertheless limited to the price of the relevant goods or services purchased from us.